

MASTER ALLOYS FOR HOT DIPPING GALVANIZING

[a] CHEMICAL COMPOSITION:

| Chemical composition: | | | | | | | | | |
|-----------------------|--------------|-------------|--------------|--------------|--------------|--------------|--------------|--------------|---------|
| | Al | Sb | Cu | Mg | Pb | Fe | Cd | Sn | Zn |
| ZnAl5 | 4.5 5.5 | - | 0.030 max | 0.020 max | 0.010 max | 0.020 max | 0.003 max | 0.001 max | balance |
| ZnAl10 | 9.5 10.5 | - | 0.030 max | 0.020 max | 0.010 max | 0.020 max | 0.003 max | 0.001 max | balance |
| ZnSb5 | 0.005 max | 4.5 5.5 | 0.005 max | 0.005 max | 0.020 max | 0.050 max | 0.003 max | 0.005 max | balance |
| ZnSb10 | 0.005 max | 9.5 10.5 | 0.005 max | 0.005 max | 0.020 max | 0.050 max | 0.003 max | 0.005 max | balance |

[b] PACKAGE:

- Ingot: 5.5 kg / 580x70x40 mm
- Packing: 500 kg / 580x580x580 mm (on pallet)

